

PRODUCT INFOSHEET: Duro-Glide® Reprocessed #595 Blue

Duro-Glide® Reprocessed #595 Blue is a UHMW repro polymer mix. The material is impregnated with an industrial lubricant creating an improved low coefficient of friction (non-stick surface) that makes it ideal for lining applications where sticking or caking of bulk goods can create a build-up of material.

PROPERTIES

Excellent Sliding Properties | Low Coefficient of Friction | Good Notched Impact Strength
No Sticking or Caking of Bulk Materials | Weldable

INDUSTRY / APPLICATIONS

Bulk Goods Handling | Conveyor Industry (Earthmoving Equipment) | Truck Liners, Hoppers, Chutes | Rail Road Car Liners
Gypsum Industry | Cement Industry

COLOR

#595 Blue Reprocessed

CHARACTERISTICS AND STANDARD VALUES

Physical Properties	Method	SI Unit	SI Value
Density	ASTM D792 ISO 1183-1	g/cc g/cm ³	> 0.93 > 0.93
Abrasion (Sand-Slurry-Test rel. to GUR 4120 = 100%)	ISO 15527	% (Average)	130 (± 10%)
Notched Impact Strength	ISO 11542-2	mJ/mm ² kJ/m ²	> 80
Tensile Strength, Yield	ASTM D638 ISO 527-2	Psi MPa	> 2500 > 17
Break Elongation	ASTM D638 ISO 527-2	% %	> 100 > 50
Creep properties under varying compressive stress: Creep < 10%	Max.	Psi MPa	1450 10
Coefficient of Friction, ASTM 1894 Metal= Rz 2,5 µ, Pm= 2 N/mm ² , V= 150 mm/min	Static Dynamic	µ µ	0.16 0.10
Shore-hardness, 3-s-value 6mm plate	ASTM D2240 ISO 868 / DIN 53505	D D	62 62
Water Absorption	--	%	< 0.1 (Nil)
Flammability	UL 94	--	HB
Thermal Properties			
Melt Temperature	ASTM 3417 (DSC) ISO 3146 (DSC)	°F °C	275 - 278 135 - 137
Permanent Operation Temp., Max.	--	°F °C	176 80
Coefficient of Linear Expansion	ASTM D696 DIN 53752	73 – 176 °F 23 – 80°C	≈ 1.1x10 ⁻⁴ /°F ≈ 2.0x10 ⁻⁴ /°C
Electrical Properties			
Surface Resistivity	ASTM D257 IEC 93	Ohm Ω	> 10 ¹⁴ > 10 ¹⁴
Volume Resistivity	ASTM D257 IEC 93	Ohm-cm Ω * cm	> 10 ¹⁴ > 10 ¹⁴

Any suggestions or recommendations for the use of our products are based on tests believed to be reliable and on the independent judgment of our technicians. However, it is ultimately up to the Customer/End User to determine whether the product(s) provided by Duro-Glide® are suitable for the intended purpose or application. Duro-Glide® Polymer Sheets makes no warranty of fitness for a particular purpose, nor does it guarantee the results to be obtained. Nothing in this literature is intended as a recommendation to use our products so as to infringe on any patent.